

Eco Solvent Poster Art Paper 210gsm Graphic Art Range IFA 145

Product Description

Eco Solvent, Latex and UV ink compatible, natural white, lightweight fourdrinier art paper. Ideal for posters and producing art prints for the décor market.

Features

- Natural white
- Soft textured 'etching paper' surface
- Eco Solvent, Latex and UV ink compatible
- Archival - acid and lignin free
- Excellent colour reproduction with deep blacks
- Easy handling for shipping prints in tubes

Applications

- Art posters
- Décor art prints
- Open edition prints
- Promotional posters
- Trade show displays

Basic Weight (gsm)	210		
Paper Thickness (Microns)	280	Paper Thickness (Inches)	0.008
Base Material	Alpha Cellulose		
Coating Type	Matte		
Ink Type	Eco Solvent, UV and Latex Ink		
Surface Texture	Soft Textured 'Etching Paper'		
Whiteness (CIE)	96.8		
Brightness (TAPPI)	86		
OBA Content	No		
Opacity (%)	96		
pH	7.5-9.5		
Recyclable	Yes		
Notes			

Sheets	
Rolls (30m Length, 3" Core)	60", 54", 30"

Additional Sizes are available on request, subject to order quantity.

Handling and Storage

- All digital fine art medias are fragile and need to be handled with care. Try not to touch the surface of the paper, always hold the paper by the edges and wear cotton gloves if necessary.
- Return unused material to the original box and only store finished prints in archival quality packaging. If mounting or framing, use only archive grade tapes and glues.
- After printing, leave prints open to the air to fully dry (24 hours is recommended). Do not stack prints on top of each other straight away.
- Using a giclée varnish or spray will help protect your print from damage, effects of UV light and environmental attack.

Conditions of Use

- The recommended climate for storage of all papers is 15-20°C, relative humidity of 40-60%. Always store in original packaging, out of direct sunlight and protected from moisture.
- Do not exceed temperatures of 82°C (180°F) when dry mounting.

All recommendations are for your guidance only. These are subject to our test criteria, which remain subject to change without prior notice.