

Uncoated Papers

LFM098 Top Colour Paper - FSC® 160 g/m²

Toner
CrystalPoint
(eco) Solvent
UV Curable
Latex

Product Description

A high white, smooth, FSC-certified, uncoated paper for high quality drawings and posters.

Physical Properties

Weight (g/m ²)	160		Brightness (%)	113	D 65/10°
Opacity (%)	99	ISO 2471	Whiteness (%)	168	CIE D65/10
Bulk (cm ³ /g)	1.23	ISO 534	Roughness (ml/min)	200	Bendtsen

Applications/features

Indoor posters
Point of Purchase
CAD/GIS
FSC certified
EU Ecolabel
ISO 9706 standard for permanence
EMAS and ISO 14001 certified

Available Widths (mm)

3"core	700	841	914	1067															
--------	-----	-----	-----	------	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--

Refer for our current offering to mediaguide.oce.com

Storage Conditions

Shelf life: 2 years, Temperature 21°C, Relative Humidity 50%
Repack opened rolls when not in use. Allow material to adapt to room conditions for 24 hours before printing.

Print Conditions

Best results are obtained between 20-27°C and 30-60% RH.

Environment, Health & Safety

No Material Safety Data Sheet required. Paper waste suitable for recycling.

Lamination Compatibility

Cold	Warm	Hot	Cold: pressure sensitive Warm: heat activated: 85°C - 95°C Hot: heat activated: 105°C -130°C
yes	yes	yes	

Outdoor Use

This uncoated paper is developed for indoor use.

Colour Profiles

Canon develops high-quality colour profiles for media / ink / printer / RIP combinations.
Check availability of profiles for your printer on mediaguide.oce.com



Processing Guidelines

Printing guidelines

Allow material to adapt to room conditions for 24 hours before printing.

It is recommended to handle the media with cotton gloves. Make sure that the media does not come into contact with grease, oil, silicon, and dirt to avoid printing defects.

Insert media with care in the printers. Incorrect loading can cause skewing or creasing. Allow material to adapt to room conditions for 24 hours before printing. It is recommended to calibrate the printer before printing and to make a test print. Print results will vary for different printers.

Ink/toner restrictions and printer settings have to be set for specific printers to obtain the best results. Canon colour profiles include recommended ink restrictions and printer settings for Canon supported printers.

Finishing guidelines

When laminating Océ CrystalPoint® prints pressure sensitive laminates are recommended.

A laminator with soft rubber rollers is preferred. For optimal results temperature should be set between 55-60°C.

Standard disclaimer:

All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.