

CrystalPoint

Water

(eco) Solvent

UVgel (matte)

Latex

LFM331 Tyvek

105 g/m²

Product Description

Robust, highly tear resistant banner composed of flash spun high-density polyethylene fibres. This uncoated Tyvek is printable with the CrystalPoint Technology and on Colorado1650 in matte mode Tyvek® is a DuPont trademark.

Physical Properties

Thickness	270 µm	ISO 534	Tear Strength MD/CD	7.6 / 7.2 N	DIN 21974
Weight	105.0 g/m ²	ISO 536	Elongation MD/CD	19 / 22 %	ISO 1924-2
Tensile strength MD/CD	290/325 N/inch	ISO 1924-2	Opacity	98.4 %	ISO 2471

All values listed are target values

Applications/features

Indoor/outdoor posters
Event banners, Maps
Labels

Excellent print quality
PVC free, suited for recycling
High tear resistance
Suitable for grommets or sewing

Available Widths (mm)

3" core	914	1067								
---------	-----	------	--	--	--	--	--	--	--	--

Refer for our current offering to www.canon-europe.com/mediaguide

Storage Conditions

Shelf life: 1 year, Temperature 22°C, Relative Humidity 50%
Repack opened rolls when not in use.

Print Conditions

Best results are obtained between 20 ± 3°C and 50 ± 5% RH.
Refer also to printer specifications.

Environment, Health & Safety

No Material Safety Data Sheet required. Tyvek is suitable for recycling.

Lamination Compatibility

Cold	Warm	Hot
yes	no	no

Cold: pressure sensitive
Warm: heat activated: 85°C - 95°C
Hot: heat activated: 105°C -130°C

Outdoor Use

Tyvek is developed for outdoor use. Tyvek printed with CrystalPoint technology can be used outdoor for short term applications (3-4 weeks).

Colour Profiles

Canon develops high-quality colour profiles for media / ink / printer / RIP combinations.
Check availability of profiles for your printer on www.canon-europe.com/mediaguide

Processing Guidelines

Printing guidelines

Allow material to adapt to room conditions for 24 hours before printing.

It is recommended to handle the media with cotton gloves. Make sure that the media comes not into contact with grease, oil, silicon, and dirt to avoid printing defects.

Insert the Tyvek with care in the printer. Incorrect loading can cause skewing or creasing.

It is recommended to calibrate the printer before printing and to make a test print. Print results will vary for different printer ink/toner combinations. Ink/toner restrictions and printer settings have to be set for specific printer-ink/toner combinations to obtain the best results. Canon colour profiles will set optimal restrictions and printer-settings for Canon supported printers.

Because of the random/non oriented fibers Tyvek has a certain inhomogeneity across its web. This inhomogeneity may differ per batch and may lead to problems on printers, specifically in cases where Tyvek is exposed to heat.

Due to the nature of the product, high tolerance on thickness, only CW700 and CW3700 are recommended.

Application guidelines

Pressure-sensitive adhesive tabs of Tyvek® or Mylar® polyester film wrapped around a sewn seam at each edge will reduce the possibility of edge tear.

It is recommended that the Tyvek banners are stitched hem side up so that the sewing machine comes only in contact with the unprinted side of the banner. Use 1.2 to 2 stitches/cm at low tension to eliminate skipping.

When sewing banners, avoid stitches at or near the edge to reduce the chance for edge-tear.

When applying grommets, they should be inserted in double hemmed edges. Corner grommets should be placed where the length and width hems cross, so that the grommet is embedded in four layers.

Standard disclaimer:

All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.

Canon Inc.
canon.com

Canon Europe
canon-europe.com

English edition 0615

© Canon Europa N.V., 2020

The Canon logo is displayed in its characteristic red color and bold, sans-serif font.